

Hardener

Thinning agent for FIBROLIT® ZWO

Injection gun for FIBROFIX®-SECHS

280.05 Hardener

Description:

Individual hardener for 280.02 FIBROLIT®-ZWO tool casting resin or for use with epoxy resin
280.24 thinning agent for FIBROLIT®-ZWO.

Bottle, 50ml



280.24 Thinning agent for FIBROLIT® ZWO

Description:

To increase the flow properties of FIBROLIT® ZWO tool casting resin, the thinner (pure epoxy resin) can be added in a specific ratio (max. 5% = 45 g).

It must be noted that the addition of thinner will extend the curing time.

The thinner can also be used together with hardener 280.05 as a casting resin. A resin/hardener mixing ratio of 5:1 (by weight) must be observed.

Can, 500 ml



280.09 Injection gun for FIBROFIX®-SECHS

Description:

For simple application of FIBROFIX®-SECHS 280.08.

The casting resin cartridge is compressed by means of a threaded spindle and removed from the injection gun after emptying.

